



DS Bronze 20X

Optical & Solar Properties

	Single Pane	Double Pane
Visible Light Transmitted	16%	15%
Visible Light Reflected (interior)	46%	47%
Visible Light Reflected (exterior)	39%	40%
Ultra Violet Block	99%	99%
Total Solar Energy Reflected	64%	64%
Total Solar Energy Transmitted	9%	8%
Total Solar Energy Absorbed	27%	28%
Emissivity (Room Side)	0.84	0.84
Glare Reduction	82%	81%
Selective InfraRed Reduction (SIRR)	96%	96%
InfraRed Energy Rejection (IRER)	92%	92%
Shading Coefficient	0.20	0.14
Solar Heat Gain Coeff. (G-Value)	0.17	0.12
U-Value Winter (IP)	1.04	0.48
U-Value Winter (SI)	5.91	2.73
Luminous Efficacy	0.83	1.06
Total Solar Energy Rejected	83%	88%

R069B2X - Pressure Sensitive Adhesive

For more information please contact

Kingston Coatings, LLC

Sidney McAlister 615-491-4265

Main 615-952-4903 Text 24/7 615-330-5294

sales@kingstoncoatings.com

www.kingstoncoatings.com

