



DR Grey 35X

Optical & Solar Properties

	Single Pane	Double Pane
Visible Light Transmitted	36%	32%
Visible Light Reflected (interior)	14%	21%
Visible Light Reflected (exterior)	22%	23%
Ultra Violet Block	99%	99%
Total Solar Energy Reflected	26%	27%
Total Solar Energy Transmitted	31%	26%
Total Solar Energy Absorbed	44%	47%
Emissivity (Room Side)	0.84	0.84
Glare Reduction	61%	61%
Selective InfraRed Reduction (SIRR)	71%	71%
InfraRed Energy Rejection (IRER)	58%	58%
Shading Coefficient	0.50	0.40
Solar Heat Gain Coeff. (G-Value)	0.43	0.35
U-Value Winter (IP)	1.04	0.48
U-Value Winter (SI)	5.91	2.73
Luminous Efficacy	0.70	0.80
Total Solar Energy Rejected	57%	65%

R070W5X - Pressure Sensitive Adhesive

For more information please contact

Kingston Coatings, LLC

Sidney McAlister 615-491-4265

Main 615-952-4903 Text 24/7 615-330-5294

sales@kingstoncoatings.comwww.kingstoncoatings.comPowered by
NanoTechnology