



DR Grey 10X

Optical & Solar Properties

	Single Pane	Double Pane
Visible Light Transmitted	8%	7%
Visible Light Reflected (interior)	17%	23%
Visible Light Reflected (exterior)	55%	55%
Ultra Violet Block	99%	99%
Total Solar Energy Reflected	58%	58%
Total Solar Energy Transmitted	7%	6%
Total Solar Energy Absorbed	35%	36%
Emissivity (Room Side)	0.84	0.84
Glare Reduction	91%	91%
Selective InfraRed Reduction (SIRR)	93%	93%
InfraRed Energy Rejection (IRER)	83%	83%
Shading Coefficient	0.20	0.14
Solar Heat Gain Coeff. (G-Value)	0.17	0.12
U-Value Winter (IP)	1.04	0.48
U-Value Winter (SI)	5.91	2.73
Luminous Efficacy	0.40	0.50
Total Solar Energy Rejected	83%	88%

R070W0X - Pressure Sensitive Adhesive

For more information please contact

Kingston Coatings, LLC

Sidney McAlister 615-491-4265

Main 615-952-4903 Text 24/7 615-330-5294

sales@kingstoncoatings.com

www.kingstoncoatings.com



Powered by
NanoTechnology

