

NT PerLite Ceramic 70i - Neutral Interior Films

Low reflectance, high performance

NT PerLite Ceramic 70i is a highly durable, ceramic-based interior window film. NT PerLite Ceramic 70i was developed using a proprietary patented advanced ceramic coating technology. As a result, its attractive neutral grey color delivers excellent solar energy rejection, with surprisingly low visible light reflectance. This makes NT PerLite Ceramic 70i an ideal solution for economic energy-saving projects when it's important to preserve view and retain a natural appearance - both inside and out. NT PerLite Ceramic 70i is particularly popular in residential and commercial projects.

| Optical and Solar Properties** | NT PerLite Ceramic 70i | |
|-------------------------------------|------------------------|--------|
| Item Number | R069L4W | |
| Pane | Single | Double |
| Visible Light Transmitted | 68% | 61% |
| Visible Light Reflected (Interior) | 9% | 12% |
| Visible Light Reflected (Exterior) | 10% | 17% |
| Ultra Violet Block | 99% | 99% |
| Total Solar Energy Reflected | 10% | 15% |
| Total Solar Energy Transmitted | 59% | 50% |
| Total Solar Energy Absorbed | 31% | 35% |
| Emissivity (Room Side) | 0.91 | 0.91 |
| Glare Reduction | 25% | 25% |
| Selective InfraRed Reduction (SIRR) | 44% | 44% |
| InfraRed Energy Rejection (IRER) | 33% | 33% |
| Shading Coefficient | 0.79 | 0.79 |
| Solar Heat Gain Coeff. (G-Value) | 0.69 | 0.68 |
| U-Value Winter (IP) | 1.08 | 0.49 |
| U-Value Winter (SI) | 6.13 | 2.78 |
| Luminous Efficacy | 0.86 | 0.78 |
| Total Solar Energy Rejected (%) | 31% | 32% |

** Performance results are calculated on 3 mm glass using NFRC methodology and LBNL Window 5.2 software, and are subject to variations in process conditions within industry standards and are only intended for estimating purposes.



Graphics

Solutions

For more information please contact **Kingston Coatings, LLC** Sidney McAlister 615-491-4265 Main 615-952-4903 Text 24/7 615-330-5294 sales@kingstoncoatings.com www.kingstoncoatings.com

S93007 4/19