



DR Grey 20X

Optical & Solar Properties

	Single Pane	Double Pane
Visible Light Transmitted	19%	18%
Visible Light Reflected (interior)	14%	21%
Visible Light Reflected (exterior)	34%	35%
Ultra Violet Block	99%	99%
Total Solar Energy Reflected	38%	38%
Total Solar Energy Transmitted	18%	15%
Total Solar Energy Absorbed	45%	47%
Emissivity (Room Side)	0.84	0.84
Glare Reduction	79%	78%
Selective InfraRed Reduction (SIRR)	82%	82%
InfraRed Energy Rejection (IRER)	70%	70%
Shading Coefficient	0.36	0.27
Solar Heat Gain Coeff. (G-Value)	0.31	0.23
U-Value Winter (IP)	1.04	0.48
U-Value Winter (SI)	5.91	2.73
Luminous Efficacy	0.54	0.66
Total Solar Energy Rejected	69%	77%

R070W6X - Pressure Sensitive Adhesive

For more information please contact

Kingston Coatings, LLC

Sidney McAlister 615-491-4265

Main 615-952-4903 Text 24/7 615-330-5294

sales@kingstoncoatings.com

www.kingstoncoatings.com



Powered by
NanoTechnology

